

GREASE COMPATIBILITY CHART

THICKENER	SULFONATE	ALUMINIUM COMPLEX	BARIUM	CALCIUM	CALCIUM 1 2-HYDROXY	CALCIUM COMPLEX	BENTONE (CLAY)	LITHIUM	LITHIUM 1 2-HYDROXY	LITHIUM COMPLEX	POLYUREA	SILICA GEL	SODIUM
SULFONATE		NC	SC	FC	FC	FC	NC	FC	FC	FC	SC	SC	NC
ALUMINIUM COMPLEX	NC		NC	NC	FC	NC	NC	NC	NC	NC	NC	FC	SC
BARIUM	SC	NC		NC	FC	SC	NC	SC	NC	SC	NC	FC	NC
CALCIUM	FC	NC	NC		FC	NC	FC	FC	SC	FC	NC	?	NC
CALCIUM 1 2-HYDROXY	FC	FC	FC	FC		SC	FC	FC	FC	FC	NC	?	NC
CALCIUM COMPLEX	FC	NC	SC	NC	SC		NC	FC	NC	FC	SC	NC	NC
BENTONE (CLAY)	NC	NC	NC	FC	FC	NC		NC	NC	NC	NC	FC	NC
LITHIUM	FC	NC	SC	FC	FC	FC	NC		FC	FC	SC	FC	NC
LITHIUM 1 2-HYDROXY	FC	NC	NC	SC	FC	NC	NC	FC		FC	NC	?	SC
LITHIUM COMPLEX	FC	NC	SC	FC	FC	FC	NC	FC	FC		SC	FC	NC
POLYUREA	SC	NC	NC	NC	NC	SC	NC	SC	NC	SC		?	NC
SILICA GEL	SC	FC	FC	?	?	NC	FC	FC	?	FC	?		NC
SODIUM	NC	SC	NC	NC	NC	NC	NC	NC	SC	NC	NC	NC	

LEGEND :

FC : FULLY COMPATIBLE

SC : SOMEWHAT COMPATIBLE - MIXTURES SOFTEN, BUT, REMAINS GREASE LIKE

NC : NOT COMPATIBLE - MIXTURES SOFTEN SEVERELY AND DO NOT REMAIN GREASE LIKE

ALL PRECAUTIONS WERE TAKEN TO ENSURE THAT THE DATA IN THESE TABLES ARE CORRECT HOWEVER, IT IS RECOMMENDED THAT YOU CONSULT THE MANUFACTURER BEFORE MIXING TWO DIFFERENT PRODUCTS